

FRblend® PP-1505

Polypropylene

Colour Image Plastic Compound Sdn. Bhd. (CIPC)

Message:

FRblend® PP-1505 is a high flow, mineral filled flame retardant polypropylene compound comply with UL94 V-2 flammability rating at 1.6mm thickness. It can be colored to meet stringent aesthetic requirements.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Colorability		
	High Flow		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	29	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	1.1 to 1.3	%	ASTM D955
Water Absorption (24 hr)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	27.0	MPa	ASTM D638
Tensile Elongation (Break)	60	%	ASTM D638
Flexural Modulus	1120	MPa	ASTM D790
Flexural Strength	36.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 4.00 mm)	40.0	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating (1.60 mm)	V-2	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	60.0 to 80.0	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	180 to 190	°C	
Middle Temperature	190 to 200	°C	

Front Temperature	200 to 210	°C
Nozzle Temperature	210 to 220	°C
Mold Temperature	30.0 to 60.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

