

3M™ Dyneon™ Fluoroelastomer FG 5630Q

Fluoroelastomer

3M Advanced Materials Division

Message:

3M™ Dyneon™ Fluoroelastomer FG 5630Q can be compounded using standard water cooled internal mixers or two-roll mills. The "dry" ingredients should be blended before adding to the masticated gum. For best results, FG 5630Q should be banded on the mill several minutes prior to adding the blended dry ingredients. Once mixed, the compounded stocks display excellent processing characteristics and storage stability.

General Information		
Additives Physical	Nominal Value	Unit
Density	1.80	g/cm³
State at Room Temperature	Solid	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

