

TRIEX® Compound 3025G20

Polycarbonate
Samyang Corporation

Message:

TRIEX® Compound 3025G20 is a Polycarbonate (PC) product. It is available in Asia Pacific, Europe, or North America. Primary characteristic: flame rated.

General Information			
UL YellowCard	E257054-521419	E121254-220609	
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	8.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.12	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	98.1	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	4900	MPa	ASTM D790
Flexural Strength (Yield)	137	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	98	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	151	°C	
1.8 MPa, Unannealed	150	°C	
CLTE - Flow	2.3E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+16	ohms · cm	ASTM D257
Dielectric Strength	31	kV/mm	ASTM D149
Dielectric Constant	3.05		ASTM D150
Dissipation Factor	9.7E-3		ASTM D150
Arc Resistance	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

