

# Selvol™ E 523S

Polyvinyl Alcohol  
Sekisui Chemical Company, Ltd.

Message:

SELVOL™ E 523S is a medium viscosity partially hydrolysed polyvinyl alcohol which finds applications principally in the Building industry.  
Building: Cement for mortars, building adhesives and gypsum boards.

General Information			
Features	Medium Viscosity		
Uses	Adhesives		
	Building Materials		
Agency Ratings	BfR Food Contact, Unspecified Rating		
	FDA Unspecified Rating		
Appearance	Off-White		
	White		
Forms	Granules		
Physical	Nominal Value	Unit	Test Method
Density	1.27 to 1.31	g/cm <sup>3</sup>	
Ash Content - Expressed as Sodium Oxide	< 0.5	wt%	Internal Method
Particle Size			Internal Method
retained 40 mesh	< 0.100	wt%	
retained 80 mesh	< 1.00	wt%	
pH - Of a 4% aqueous solution <sup>1</sup>	4.5 to 6.5		Internal Method
Viscosity - Of a 4% aqueous solution at 20°C <sup>2</sup>	23 to 27	mPa · s	Brookfield
VOC Content	< 1.0	wt%	Internal Method
Refractive Index - nD <sup>20</sup> °C	1.5200 to 1.5500		
Degree of Hydrolysis	87.0 to 89.0	mol%	Internal Method
Light Stability	Excellent		
Methanol Content	< 0.9	wt%	Internal Method
Volatiles	< 5.0	wt%	Internal Method
Thermal	Nominal Value	Unit	
Glass Transition Temperature	58.0	°C	
Melting Temperature	180	°C	
CLTE - Flow (0 to 45°C)	7.0E-5 to 1.0E-4	cm/cm/°C	
Specific Heat	1650 to 1670	J/kg/°C	
Thermal Conductivity	2.0	W/m/K	
Electrical	Nominal Value	Unit	

Volume Resistivity	3.1E+7 to 3.8E+7	ohms·cm
NOTE		
1.	International Reference: ISO 976	
2.	International Reference: ISO 2555	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

