

DESLON™ 66 DSC214GM

Polyamide 66

DESCO Co., Ltd.

Message:

Descriptions: DESLON™ DSC214GM is one of the brands which made by Polyamide66 that filled Glass Fiber/Mineral Filler 35% and reinforced goods. It provides high mechanical strength property, modification resistance, good surface appearance, thermal property.

Applications: DESLON™ DSC201AG6 is one of the most-used for good mechanical property, dimensions stability and good abrasion resistance property goods, such as Bushing of Automotive parts, etc.

General Information			
Filler / Reinforcement	Glass \mineral, 35% filler by weight		
Features	Good dimensional stability		
	High strength		
	Thermal stability, good		
Uses	Parts under the hood of a car		
	Application in Automobile Field		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.60 - 1.0	%	
Water Absorption (23°C, 24 hr)	0.70	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	124		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	108	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	6370	MPa	ASTM D790
Flexural Strength	172	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	255	°C	ASTM D648
1.8 MPa, not annealed	235	°C	ASTM D648
Melting Temperature	260	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Dielectric Strength	23	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method

Flame Rating	HB	UL 94
Injection	Nominal Value	Unit
Drying Temperature	80.0 - 100	°C
Drying Time	4.0 - 5.0	hr
Suggested Max Moisture	< 0.20	%
Rear Temperature	275 - 285	°C
Middle Temperature	285 - 290	°C
Front Temperature	285 - 295	°C
Nozzle Temperature	285 - 295	°C
Processing (Melt) Temp	285 - 295	°C
Mold Temperature	80.0 - 120	°C
Injection instructions		

Speed: 40 to 70%Pressure 1st: 30 to 60%Pressure 2nd: 30 to 60Holding Pressure: 10 to 20%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

