

LNP™ THERMOCOMP™ UX06032-WH9E041

compound

Polyphthalamide

SABIC Innovative Plastics Europe

Message:

LNP THERMOCOMP UX06032 is a compound based on Polyphthalamide resin containing Glass Fiber, Flame Retardant. Added features of this material include: Flame Retardant, Non-Brominated & Non-Chlorinated Flame Retardant, Heat Stabilized. Custom color white.

Also known as: LNP* THERMOCOMP* Compound UX06032-WH9E041

Product reorder name: UX06032-WH9E041

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Flame Retardant		
	Heat Stabilizer		
Features	Bromine Free		
	Chlorine Free		
	Flame Retardant		
	Heat Stabilized		
RoHS Compliance	RoHS Compliant		
Appearance	White		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.51	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.10 to 0.30	%	Internal Method
Water Absorption (23°C, 24 hr)	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11100	MPa	ISO 527-2/1
Tensile Stress (Break)	93.0	MPa	ISO 527-2/5
Tensile Strain (Break)	1.5	%	ISO 527-2/5
Flexural Modulus ²	9600	MPa	ISO 178
Flexural Stress	140	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ³ (23°C)	4.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁴ (23°C)	20	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵ (1.8 MPa, Unannealed, 64.0 mm Span)	265	°C	ISO 75-2/Af
Electrical	Nominal Value	Unit	Test Method

Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Glow Wire Flammability Index (1.50 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
0.800 mm	825	°C	
1.60 mm	825	°C	
3.00 mm	850	°C	
Injection	Nominal Value	Unit	
Drying Temperature	110 to 120	°C	
Drying Time	3.0 to 5.0	hr	
Rear Temperature	280 to 300	°C	
Middle Temperature	290 to 310	°C	
Front Temperature	295 to 315	°C	
Processing (Melt) Temp	305 to 315	°C	
Mold Temperature	130 to 150	°C	
Back Pressure	0.200 to 0.300	MPa	
Screw Speed	40 to 80	rpm	
NOTE			
1.	Tensile Bar		
2.	2.0 mm/min		
3.	80*10*4		
4.	80*10*4		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT