

Wellamid® GF30-60 XE-N

Polyamide 6

Wellman Engineering Resins

Message:

Wellamid® GF30-60 XE-N is a Polyamide 6 (Nylon 6) material filled with 33% glass fiber. It is available in Asia Pacific, Europe, Latin America, or North America for injection molding. Primary attribute of Wellamid® GF30-60 XE-N: Flame Rated.

Typical application of Wellamid® GF30-60 XE-N: Automotive

General Information			
UL YellowCard	E44600-235474		
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.38	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 23°C	0.60 to 1.0	%	
Flow : 23°C	0.10 to 0.50	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	180	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	3.0	%	ISO 527-2
Flexural Modulus (23°C)	9000	MPa	ISO 178
Flexural Stress (23°C)	260	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	14	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	210	°C	ISO 75-2/A
Melting Temperature (DSC)	220	°C	ISO 3146
Flammability	Nominal Value		Test Method
Flame Rating (0.750 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	260 to 282	°C	
Middle Temperature	254 to 277	°C	
Front Temperature	249 to 271	°C	
Nozzle Temperature	249 to 271	°C	
Processing (Melt) Temp	254 to 282	°C	
Mold Temperature	71.1 to 93.3	°C	

Injection Pressure	34.5 to 138	MPa
Back Pressure	0.345	MPa
Screw Speed	30 to 120	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

