

# Huaфон HF-4095A

Thermoplastic Polyurethane Elastomer (Polyether)

Huaфон Group Co., Ltd.

Message:

Operation: Injection molding, Extrusion, Calendering  
Characteristics: Excellent hydrolytic resistance, Bacteria resistance, Low temperature elastic, Aging resistance  
Applications: Tube & hose, Fabric coating, compounding, Film, Fire hose, Animal ear tag, Accessories, etc.

General Information	
Features	Bacteria Resistant
	Hydrolysis Resistant
Uses	Compounding
	Fabric Coatings
	Film
	Hose
	Molded Ear Tags
	Tubing
Processing Method	Calendering
	Compounding
	Extrusion
	Injection Molding

Hardness	Nominal Value		Test Method
Durometer Hardness (Shore A)	95		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Abrasion	65	mm <sup>3</sup>	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	13.0	MPa	ASTM D412
Tensile Strength	32.0	MPa	ASTM D412
Tensile Elongation (Break)	450	%	ASTM D412
Tear Strength	120	kN/m	ASTM D624

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

