

# Tarnoform® 300 GF2

Acetal (POM) Copolymer

Grupa Azoty S.A.

## Message:

Tarnoform® 300 GF2 there is 10% glass fibres reinforced injection-moulding grade with increased strength and stiffness and with reduced shrinkage and coefficient of linear thermal expansion.

| General Information                         |                                    |                        |             |
|---------------------------------------------|------------------------------------|------------------------|-------------|
| Filler / Reinforcement                      | Glass Fiber,10% Filler by Weight   |                        |             |
| Features                                    | High Stiffness                     |                        |             |
|                                             | High Strength                      |                        |             |
|                                             | Low Shrinkage                      |                        |             |
| Uses                                        | Appliances                         |                        |             |
|                                             | Automotive Applications            |                        |             |
|                                             | Electrical/Electronic Applications |                        |             |
|                                             | Household Goods                    |                        |             |
| Appearance                                  | Black                              |                        |             |
|                                             | Colors Available                   |                        |             |
|                                             | Natural Color                      |                        |             |
| Forms                                       | Granules                           |                        |             |
| Processing Method                           | Injection Molding                  |                        |             |
| Physical                                    | Nominal Value                      | Unit                   | Test Method |
| Density                                     | 1.49                               | g/cm <sup>3</sup>      | ISO 1183    |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)   | 7.0                                | g/10 min               | ISO 1133    |
| Melt Volume-Flow Rate (MVR) (190°C/2.16 kg) | 6.00                               | cm <sup>3</sup> /10min | ISO 1133    |
| Molding Shrinkage                           |                                    |                        | ISO 294-4   |
| Across Flow : 2.00 mm                       | 1.7                                | %                      |             |
| Flow : 2.00 mm                              | 1.6                                | %                      |             |
| Water Absorption                            |                                    |                        | ISO 62      |
| Saturation, 23°C                            | 0.80                               | %                      |             |
| Equilibrium, 23°C, 50% RH                   | 0.17                               | %                      |             |
| Hardness                                    | Nominal Value                      | Unit                   | Test Method |
| Ball Indentation Hardness (H 358/30)        | 190                                | MPa                    | ISO 2039-1  |
| Mechanical                                  | Nominal Value                      | Unit                   | Test Method |
| Tensile Modulus                             | 5100                               | MPa                    | ISO 527-2/1 |
| Tensile Stress (Yield)                      | 90.0                               | MPa                    | ISO 527-2/5 |

|                                                   |                            |                   |                    |
|---------------------------------------------------|----------------------------|-------------------|--------------------|
| Tensile Strain (Break)                            | 3.0                        | %                 | ISO 527-2/5        |
| Flexural Modulus <sup>1</sup>                     | 4400                       | MPa               | ISO 178            |
| Flexural Stress <sup>2</sup>                      | 110                        | MPa               | ISO 178            |
| <b>Impact</b>                                     | <b>Nominal Value</b>       | <b>Unit</b>       | <b>Test Method</b> |
| Charpy Notched Impact Strength                    | 3.5                        | kJ/m <sup>2</sup> | ISO 179/1eA        |
| Charpy Unnotched Impact Strength                  | 35                         | kJ/m <sup>2</sup> | ISO 179/1eU        |
| Notched Izod Impact Strength                      | 4.0                        | kJ/m <sup>2</sup> | ISO 180            |
| <b>Thermal</b>                                    | <b>Nominal Value</b>       | <b>Unit</b>       | <b>Test Method</b> |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 160                        | °C                | ISO 75-2/A         |
| Vicat Softening Temperature                       | 155                        | °C                | ISO 306/B          |
| Melting Temperature                               | 167                        | °C                | ISO 11357-3        |
| CLTE                                              |                            |                   | ISO 11359-2        |
| Flow : 23 to 55°C                                 | 6.0E-5                     | cm/cm/°C          |                    |
| Transverse : 23 to 55°C                           | 9.0E-5                     | cm/cm/°C          |                    |
| Limit of Temperature - a few hours operation      | 100                        | °C                |                    |
| Burning Rate                                      | < 100                      | mm/min            | FMVSS 302          |
| ISO Type                                          | POM-K, M-GNR, 02-003, GF10 |                   | ISO 1874           |
| <b>Electrical</b>                                 | <b>Nominal Value</b>       | <b>Unit</b>       | <b>Test Method</b> |
| Surface Resistivity                               | 1.0E+13                    | ohms              | IEC 60093          |
| Volume Resistivity                                | 1.0E+14                    | ohms·cm           | IEC 60093          |
| Electric Strength (2.00 mm)                       | 25                         | kV/mm             | IEC 60243-1        |
| Dielectric Constant (1 Hz)                        | 4.20                       |                   | IEC 60250          |
| Dissipation Factor (1 Hz)                         | 9.5E-3                     |                   | IEC 60250          |
| Comparative Tracking Index (Solution A)           | 600                        | V                 | IEC 60112          |
| <b>Flammability</b>                               | <b>Nominal Value</b>       | <b>Unit</b>       | <b>Test Method</b> |
| Flame Rating (3.20 mm)                            | HB                         |                   | UL 94              |
| <b>Injection</b>                                  | <b>Nominal Value</b>       | <b>Unit</b>       |                    |
| Drying Temperature                                | 100 to 120                 | °C                |                    |
| Drying Time                                       | 2.0 to 4.0                 | hr                |                    |
| Suggested Max Moisture                            | < 0.10                     | %                 |                    |
| Suggested Max Re grind                            | 10                         | %                 |                    |
| Processing (Melt) Temp                            | 180 to 230                 | °C                |                    |
| Mold Temperature                                  | 80.0 to 110                | °C                |                    |
| Injection Pressure                                | 80.0 to 110                | MPa               |                    |
| Injection Rate                                    | Slow-Moderate              |                   |                    |
| <b>NOTE</b>                                       |                            |                   |                    |
| 1.                                                | 2.0 mm/min                 |                   |                    |
| 2.                                                | 2.0 mm/min                 |                   |                    |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT