

Braskem PP TI4340L2

Polypropylene Impact Copolymer

Braskem America Inc.

Message:

Sub-group

Impact Copolymer

Description

Good balance of stiffness and impact strength, excellent organoleptic properties, ultra-violet stabilization

Applications

Suggested uses include compounding, thin-walled injection molding

General Information			
Additive	UV Stabilizer		
Features	Good Organoleptic Properties		
	Good UV Resistance		
	Impact Copolymer		
Uses	Compounding		
	Thin-walled Parts		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Compounding		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	27.6	MPa	ASTM D638
Tensile Elongation ² (Yield)	5.0	%	ASTM D638
Flexural Modulus - 1% Secant ³	1380	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	75	J/m	ASTM D256A
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT