

Shinite® PET T102G15

Polyethylene Terephthalate
Shinkong Synthetic Fiber Corp.

Message:

Shinite® PET T102G15 is a Polyethylene Terephthalate (PET) material filled with 15% glass fiber. It is available in North America.
Important attributes of Shinite® PET T102G15 are:
Flame Rated
Flame Retardant

General Information			
UL YellowCard	E107536-218560		
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Features	Flame Retardant		
UL File Number	E107536		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52	g/cm³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.40 to 0.70	%	
Across Flow	0.60 to 1.0	%	
Water Absorption (23°C, 24 hr)	0.15	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	98.1	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	6080	MPa	ASTM D790
Flexural Strength (Yield)	137	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	195	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant	4.00		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT