

RTP ESD 4080

Polyphthalamide

RTP Company

Message:

Carbon Fiber - Electrically Conductive - ESD Protection

| General Information | | | |
|---|--|-------------------|------------------|
| Filler / Reinforcement | Carbon fiber reinforced material | | |
| Features | Conductivity Electrostatic discharge protection | | |
| RoHS Compliance | Contact manufacturer | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.28 | g/cm ³ | ASTM D792 |
| Molding Shrinkage - Flow (3.20 mm) | 0.10 - 0.20 | % | ASTM D955 |
| Moisture Content | 0.050 | % | |
| Static Decay ¹ | | sec | FTMS 101C 4046.1 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 17200 | MPa | ASTM D638 |
| Tensile Strength | 234 | MPa | ASTM D638 |
| Tensile Elongation (Yield) | 1.0 - 2.0 | % | ASTM D638 |
| Flexural Modulus | 15200 | MPa | ASTM D790 |
| Flexural Strength | 331 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (3.20 mm) | 53 | J/m | ASTM D256 |
| Unnotched Izod Impact (3.20 mm) | 530 | J/m | ASTM D4812 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 277 | °C | ASTM D648 |
| Electrical | Nominal Value | Unit | Test Method |
| Surface Resistivity | | | |
| -- | < 1.0E+10 | ohms | ASTM D257 |
| -- | < 1.0E+9 | ohms | ESD STM11.11 |
| Volume Resistivity | < 1.0E+6 | ohms · cm | ASTM D257 |
| Injection | Nominal Value | Unit | Test Method |
| Drying Temperature | 107 | °C | |
| Drying Time | 4.0 - 6.0 | hr | |
| Dew Point | -31.7 | °C | |
| Processing (Melt) Temp | 302 - 329 | °C | |

| | | |
|--------------------------------|------------|-----|
| Mold Temperature | 135 - 163 | °C |
| Injection Pressure | 68.9 - 124 | MPa |
| Injection instructions | | |
| Desiccant Type Dryer Required. | | |
| NOTE | | |

1. MIL-PRF-81705D, 5kV to 50 V, 12% RH

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

