

# LAPEROS® B230

Liquid Crystal Polymer

Polyplastics Co., Ltd.

Message:

High Rigidity, CF reinforced

General Information			
UL YellowCard	E106764-218420		
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight		
Features	High Rigidity		
UL File Number	E106764		
Part Marking Code (ISO 11469)	>LCP-CF30<		
Physical	Nominal Value	Unit	Test Method
Density	1.49	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>1</sup>			Internal Method
Across Flow : 1.00 mm	0.18	%	
Flow : 1.00 mm	-0.050	%	
Water Absorption (23°C, 24 hr)	0.080	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	245	MPa	ASTM D638
Tensile Elongation (Break)	0.90	%	ASTM D638
Flexural Modulus	30000	MPa	ISO 178
Flexural Stress	300	MPa	ISO 178
Flexural Strain	1.1	%	ISO 178
Color Number	BK430P		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m <sup>2</sup>	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	240	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	7.0E+2	ohms · cm	Internal Method
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
NOTE			

1. 80x80x1 mm; Inj. Pressure 79MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

