

Riblene® FL 34 E

Low Density Polyethylene

Versalis S.p.A.

Message:

Riblene FL 34 E is a low density polyethylene (LDPE), additivated with slip and antiblocking agent, suitable for blown film extrusion. Riblene FL 34 E is characterised by a good balance between processability, mechanical and optical properties.

Films manufactured by Riblene FL 34 E are easily heat shrinkable.

Main Application

Riblene FL 34 E is recommended for general blown film applications, for the production of low gauge film and shrink film, and for blend.

General Information			
Additive	Antiblock Slip		
Features	Antiblocking Food Contact Acceptable Good Heat Shrinkability Good Processability Low Density Opticals Slip		
Uses	Blending Film Shrink Wrap		
Agency Ratings	EU Food Contact, Unspecified Rating		
Forms	Pellets		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.923	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.1	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (vs. Itself - Dynamic, Blown Film)	0.11		ISO 8295
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	40	µm	
Film Thickness - Recommended / Available	25 to 80 µm		
Tensile Modulus			ISO 527-3
1% Secant, MD : 40 µm, Blown Film	180	MPa	
1% Secant, TD : 40 µm, Blown Film	190	MPa	

Tensile Stress			ISO 527-3
MD : Yield, 40 µm, Blown Film	11.0	MPa	
TD : Yield, 40 µm, Blown Film	11.0	MPa	
MD : Break, 40 µm, Blown Film	23.0	MPa	
TD : Break, 40 µm, Blown Film	18.0	MPa	
Tensile Elongation			ISO 527-3
MD : Break, 40 µm, Blown Film	300	%	
TD : Break, 40 µm, Blown Film	580	%	
Dart Drop Impact ¹ (40 µm, Blown Film)	130	g	ISO 7765-1
Elmendorf Tear Strength ²			ISO 6383-2
MD : 40.0 µm	80.0	kN/m	
TD : 40.0 µm	50.0	kN/m	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -75.0	°C	ASTM D746
Vicat Softening Temperature	93.0	°C	ISO 306/A
Melting Temperature	113	°C	Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 40.0 µm, Blown Film)	70		ASTM D2457
Haze (40.0 µm, Blown Film)	6.0	%	ISO 14782
Extrusion	Nominal Value	Unit	
Melt Temperature	160 to 190	°C	
NOTE			
1.	F50		
2.	Blown Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT