

# EL-Pro™ P750J

Polypropylene Random Copolymer

SCG Chemicals Co., Ltd.

## Message:

EL-Pro P750J is a general random copolymer polypropylene resin which has high clarity and contains anti-static agent suitable for injection molding process.

General Information			
Additive	Antistatic property		
Features	Highlight		
	Antistatic property		
	Workability, good		
	The smell is low to none		
	Definition, high		
	Compliance of Food Exposure		
	Random copolymer		
Uses	Household goods		
	Food container		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow: 2.00mm	1.4	%	ASTM D955
Transverse flow: 2.00mm	1.4	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength - Across Flow <sup>1</sup>			ASTM D638
Yield	29.4	MPa	ASTM D638
Fracture	21.6	MPa	ASTM D638
Tensile Elongation (Break)	500	%	ASTM D638
Flexural Modulus	1180	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	39	J/m	ASTM D256
23°C	69	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	90.0	°C	ASTM D648
1.8 MPa, not annealed	50.0	°C	ASTM D648
Brittleness Temperature	-20.0	°C	ASTM D746
Vicat Softening Temperature	130	°C	ASTM D1525
Melting Temperature	150	°C	ASTM D2117
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Gloss	77		ASTM D2457
Haze	12	%	ASTM D1003
Injection	Nominal Value	Unit	
Processing (Melt) Temp	230 - 270	°C	
Mold Temperature	25.0 - 70.0	°C	
Injection Rate	Fast		
Screw Speed	40 - 70	rpm	
Injection instructions			
Injection Pressure: 40 to 80% of max. pressurePacking and Holding Pressure: 30 to 60% of max. pressureBack Pressure: 10% of max. pressure			
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT