

POLYPRO® SB9108H

Polypropylene Copolymer

YUHWHA Korea Petrochemical Ind. Co., Ltd.

Message:

POLYPRO® SB9108H is a Polypropylene Copolymer (PP Copolymer) material. It is available in Asia Pacific for injection molding.

Important attributes of POLYPRO® SB9108H are:

Flame Rated

RoHS Compliant

Copolymer

High Gloss

High Stiffness

Typical applications include:

Automotive

Electrical/Electronic Applications

Food Contact Applications

General Information			
Features	Block Copolymer Good Impact Resistance High Gloss High Stiffness		
Uses	Automotive Applications Electrical/Electronic Applications		
Agency Ratings	FDA Food Contact, Unspecified Rating		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.4 to 1.8	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	97		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	29.4	MPa	ASTM D638
Tensile Elongation (Break)	> 200	%	ASTM D638
Flexural Modulus	1470	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	29	J/m	
25°C	98	J/m	

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	130	°C	ASTM D648
Vicat Softening Temperature	152	°C	ASTM D1525
Peak Melting Temperature	168	°C	ASTM D3418
RTI Elec	125	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating (All Colors)	HB	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

