

Hostacom X M2 T20/3

Polyolefin
LyondellBasell Industries

Message:
Hostacom X M2 T20/3 is a Polyolefin product. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America. Typical application: Automotive.

General Information			
Uses	Automotive Applications		
	Automotive Interior Parts		
Appearance	Colors Available		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.02	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	6.00	cm ³ /10min	ISO 1133
Molding Shrinkage	0.90 to 1.1	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	42.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant	1500	MPa	ISO 527-2
Tensile Stress			ISO 527-2/50
Yield	18.0	MPa	
Break	12.0	MPa	
Tensile Strain			ISO 527-2/50
Yield	3.5	%	
Break	20	%	
Flexural Modulus - Secant	1550	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	6.0	kJ/m ²	
0°C	13	kJ/m ²	
23°C	50	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	90	kJ/m ²	
0°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			

0.45 MPa, Unannealed	90.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	53.0	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT