THERMOLAST® M TM3LFT (Series: MC/LF)

Thermoplastic Elastomer

KRAIBURG TPE

Message:

The MC/LF Series is your material solution for applications requiring basic medical approvals such as ISO 10993-5. The series convinces due to its extremely low friction coefficient. The compounds are produced exclusively by a special medical unit and available in translucent colors. Typical applications
Mechanical components
Seals
Syringe gaskets
Material advantages
Adhesion to PP
DMF listed
Excellent mechanical properties
For injection molding
KRAIBURG TPE Medical service package (description below)
Sterilizable (autoclave 134°C, gammaradiation 2x35 kGy, EtO)
Tested according to ISO 10993-5

General Information				
Features	Autoclave Sterilizable			
	Ethylene Oxide Sterilizable			
	Good Adhesion			
	Low Friction			
	Radiation Sterilizable			
Uses	Gaskets			
	Medical/Healthcare Applications			
	Seals			
Agency Ratings	DMF 25607			
	ISO 10993 Part 5			
Appearance	Translucent			
Processing Method	Extrusion			
	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	0.890	g/cm³	ISO 1183	
Hardness	Nominal Value	Unit	Test Method	
Shore Hardness (Shore A)	29		ISO 7619	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress ¹ (Yield)	4.00	MPa	ISO 37	
Tensile Elongation ² (Break)	700	%	ISO 37	

Tear Strength ³	7.0	kN/m	ISO 34-1	
Compression Set ⁴			ISO 815	
23°C, 72 hr	14	%		
70°C, 24 hr	26	%		
100°C, 24 hr	41	%		
Extrusion	Nominal Value	Unit		
Drying Temperature	60.0 to 80.0	°C		
Drying Time	2.0 to 4.0	hr		
Cylinder Zone 1 Temp.	160	°C		
Cylinder Zone 2 Temp.	180	°C		
Cylinder Zone 3 Temp.	200	°C		
Die Temperature	200 to 230	°C		
NOTE				
1.	Type S2, 200 mm/min	Type S2, 200 mm/min		
2.	Type S2, 200 mm/min			
3.	Method Bb, Angle (Nicked)			
4.	Method A			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

