Axiall PVC 1601

Flexible Polyvinyl Chloride **Axiall Corporation**

Message:

1601 is a flexible extrusion PVC compound formulated for exceptional clarity in USP Class VI applications. The compound possesses excellent color retention in applications requiring gamma radiation sterilization.

| General Information | | | |
|---------------------------------------|------------------|----------|-------------|
| Features | Good flexibility | | |
| | Definition, high | | |
| | | | |
| Agency Ratings | USP Class VI | | |
| Processing Method | Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.18 - 1.22 | g/cm³ | ASTM D792 |
| Melt Mass-Flow Rate (MFR) (175°C/14.9 | | | |
| kg) | 130 | g/10 min | ASTM D1238 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 10 sec) | 59 - 65 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | | | ASTM D638 |
| | 14.8 | MPa | ASTM D638 |
| 100% strain | 5.17 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 430 | % | ASTM D638 |
| Thermal | Nominal Value | Unit | |
| Melting Temperature | 166 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

