

# LIHAN® A601

Polyamide 66  
Nanjing Lihan Chemical Co., Ltd.

Message:  
LIHAN® A601 is a Polyamide 66 (Nylon 66) product. It can be processed by injection molding and is available in Asia Pacific. Primary characteristic: flame rated.

| General Information                             |                  |                   |                   |             |
|-------------------------------------------------|------------------|-------------------|-------------------|-------------|
| Forms                                           |                  | Pellets           |                   |             |
| Processing Method                               |                  | Injection Molding |                   |             |
| Physical                                        | Dry              | Conditioned       | Unit              | Test Method |
| Density                                         | 1.09             | --                | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage                               | 1.3 to 1.6       | --                | %                 |             |
| Water Absorption<br>(Equilibrium, 23°C, 50% RH) | 1.0 to 1.4       | --                | %                 | ISO 62      |
| Water Content                                   | 7.0 to 8.0       | --                | %                 | ISO 62      |
| Hardness                                        | Dry              | Conditioned       | Unit              | Test Method |
| Rockwell Hardness<br>(R-Scale)                  | 110              | 100               |                   | ISO 2039-2  |
| Mechanical                                      | Dry              | Conditioned       | Unit              | Test Method |
| Tensile Stress (Break)                          | 55.0             | 40.0              | MPa               | ISO 527-2   |
| Tensile Strain (Break)                          | 40               | 60                | %                 | ISO 527-2   |
| Flexural Modulus                                | 2100             | 1000              | MPa               | ISO 178     |
| Flexural Stress                                 | 65.0             | 30.0              | MPa               | ISO 178     |
| Impact                                          | Dry              | Conditioned       | Unit              | Test Method |
| Notched Izod Impact<br>Strength                 | 20               | --                | kJ/m <sup>2</sup> | ISO 180     |
| Thermal                                         | Dry              | Conditioned       | Unit              | Test Method |
| Heat Deflection<br>Temperature                  |                  |                   |                   |             |
| 0.45 MPa, Unannealed                            | 200              | --                | °C                | ISO 75-2/B  |
| 1.8 MPa, Unannealed                             | 60.0             | --                | °C                | ISO 75-2/A  |
| Melting Temperature                             | 260              | --                | °C                | DSC         |
| CLTE - Flow                                     | 7.0E-5 to 1.0E-4 | --                | cm/cm/°C          | ASTM D696   |
| Electrical                                      | Dry              | Conditioned       | Unit              | Test Method |
| Surface Resistivity                             | 1.0E+13          | 1.0E+10           | ohms              | ASTM D257   |
| Dielectric Strength                             | 20               | --                | kV/mm             | ASTM D149   |
| Flammability                                    | Dry              | Conditioned       | Unit              | Test Method |
| Flame Rating (1.59 mm)                          | HB               | --                |                   | UL 94       |
| Injection                                       | Dry              | Unit              |                   |             |
| Processing (Melt) Temp                          | 255 to 290       |                   | °C                |             |
| Mold Temperature                                | 40.0 to 80.0     |                   | °C                |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

