

LNP™ KONDUIT™ OX10324 compound

Polyphenylene Sulfide

SABIC Innovative Plastics Asia Pacific

Message:

LNP KONDUIT* OX10324 is a compound based on PPS resin. Added feature of this grade is: Thermally Conductive.

Also known as: LNP* KONDUIT* Compound OX10324

Product reorder name: OX10324

General Information			
UL YellowCard	E207780-100960980		
Features	Thermally Conductive		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.75	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 24 hr	0.10 to 0.30	%	
Flow : 24 hr	0.10 to 0.20	%	
Water Absorption (23°C, 24 hr)	0.010	%	Internal Method, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	13500	MPa	ASTM D638
--	14000	MPa	ISO 527-2/1
Tensile Strength			
Break ²	49.0	MPa	ASTM D638
Break	53.0	MPa	ISO 527-2/5
Tensile Elongation			
Break ³	0.60	%	ASTM D638
Break	0.60	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁴	15600	MPa	ASTM D790
-- ⁵	13500	MPa	ISO 178
Flexural Stress			
--	73.0	MPa	ISO 178
Break, 50.0 mm Span ⁶	75.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	24	J/m	ASTM D256
23°C ⁷	3.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	70	J/m	ASTM D4812
23°C ⁸	7.0	kJ/m ²	ISO 180/1U

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	275	°C	ASTM D648
1.8 MPa, Unannealed, 6.40 mm	258	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁹	231	°C	ISO 75-2/Af
Ball Pressure Test (165°C)	Pass		IEC 60695-10-2
CLTE			
Flow : -40 to 40°C	1.3E-5	cm/cm/°C	ASTM E831
Flow : -30 to 80°C	1.3E-5	cm/cm/°C	ISO 11359-2
Flow : 23 to 80°C	1.4E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	2.5E-5	cm/cm/°C	ASTM E831
Transverse : -30 to 80°C	2.4E-5	cm/cm/°C	ISO 11359-2
Transverse : 23 to 80°C	2.4E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity			
-- ¹⁰	3.5	W/m/K	ASTM E1461
-- ¹¹	15	W/m/K	ASTM E1461
-- ¹²	1.3	W/m/K	ISO 22007-2
-- ¹³	18	W/m/K	ISO 22007-2
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI Str	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 2.5E+4	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.20 mm)	V-0		UL 94
Glow Wire Ignition Temperature (1.00 mm)	850	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Suggested Shot Size	50 to 75	%	
Rear Temperature	316 to 343	°C	
Middle Temperature	316 to 343	°C	
Front Temperature	316 to 343	°C	
Processing (Melt) Temp	321 to 349	°C	
Mold Temperature	110 to 150	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	60 to 100	rpm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	1.3 mm/min		

5.	2.0 mm/min
6.	1.3 mm/min
7.	80*10*4
8.	80*10*4
9.	80*10*4 mm
10.	through-plane, 10*10*3mm sample
11.	in-plane, ø25*0.4mm disc
12.	through-plane, 60*60*3mm plaque
13.	in-plane, 60*60*3mm plaque

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

