

# PRIMALLOY® A1706

Thermoplastic Elastomer

Mitsubishi Chemical Performance Polymers, Inc.

## Message:

PRIMALLOY® A1706 is a Thermoplastic Elastomer (TPE) material. It is available in Asia Pacific, Europe, or North America.

General Information			
Physical	Nominal Value	Unit	Test Method
Density	1.02	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Molding Shrinkage <sup>1</sup>			Internal Method
Across Flow : 2.00 mm	0.70	%	
Flow : 2.00 mm	1.3	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	77		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (Break)	9.00	MPa	ISO 37
Tensile Elongation (Break)	760	%	ISO 37
Compression Set <sup>2</sup> (70°C, 22 hr)	64	%	ISO 815
NOTE			
1.	120x120x2 mm test plaque		
2.	6 sheets (each thickness = 2mm)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

