ELASTOSIL® E 70

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, RTV-1
Smoothing Irons, Household Appliances
Bonding & Sealing, Adhesives and Sealants
Household Appliances, Household Appliances
Small Appliances, Household Appliances
Bonding & Sealing, Mechanical and Plant Engineering

General Information			
Uses	Adhesives		
	Bonding		
	Sealants		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Red		
Density			
	1.22	g/cm³	DIN 53217
	1.24	g/cm³	ISO 1183
Viscosity	60	Pa·s	Brookfield
Curing Time	12	hr	
Skin Forming Time ¹ (23°C)	15.0 to 20.0	min	
Cured Properties	Nominal Value	Unit	Test Method

DIN 53505

DIN 53504

DIN 53504

ASTM D624B

Tear Strength 5.10

NOTE

1. 50% R.H

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

MPa

kN/m

%

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

40

3.50

300

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

Shore Hardness (Shore A)

Tensile Elongation at Break

Tensile Strength

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

