

SIBUR PP H030 GP/1

Polypropylene Homopolymer

SIBUR, LLC

Message:

PP-H030-GP/1 is a polypropylene homopolymer with standard molecular weight distribution. The product is characterized by medium melt flow range, an optimal stabilization package and balanced physical and mechanical properties.

Typical Applications:

PP-H030-GP/1 is a general purpose grade, it is recommended for Injection Moulding, Extrusion and Thermoforming applications. It complies with EU Food Contact Regulations.

General Information			
Features	Homopolymer		
	Medium Flow		
Uses	General Purpose		
Agency Ratings	EC 1907/2006 (REACH)		
	EU Food Contact, Unspecified Rating		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
	Thermoforming		
Physical	Nominal Value	Unit	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	
Mechanical	Nominal Value	Unit	
Tensile Stress ¹ (Yield)	30.0	MPa	
Tensile Strain ² (Yield)	10	%	
Flexural Modulus ³	1500	MPa	
Impact	Nominal Value	Unit	
Notched Izod Impact Strength (23°C)	2.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	80.0	°C	
Vicat Softening Temperature	155	°C	ISO 306/A
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	5.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

