Dragon-Skin® 10 Fast

Silicone

Smooth-On, Inc

Message:

Dragon Skin® silicones are high performance platinum cure liquid silicone compounds that are used for a variety of applications ranging from creating skin effects and other movie special effects to making production molds for casting a variety of materials. Because of the superior physical properties and flexibility of Dragon Skin® rubbers, they are also used for medical prosthetics and cushioning applications. Dragon Skin® rubbers are also used for a variety of industrial applications and have a service temperature range of a constant -70°F to +400°F (-21°C to + 205°C).

Great for Making Molds for a Variety of Applications - Available in Shore 10A, 20A and 30A, Dragon Skin® silicones can be used to make exceptionally strong and tear resistant molds for casting plaster, wax, concrete, resins and other materials.

Time Tested, Versatile Special Effects Material - Soft, super-strong and stretchy, Dragon Skin® 10 (Fast, Medium and Slow speeds) is used around the world to make spectacular skin and creature effects. An infinite number of color effects can be achieved by adding Silc Pig® silicone pigments or Cast Magic® effects powders. Cured rubber can also be painted with the Psycho Paint® system.

Easy To Use - Dragon Skin® silicones are mixed 1A:1B by weight or volume. Liquid rubber can be thinned with Silicone Thinner® or thickened with THI-VEX® II. Rubber cures at room temperature (73°F/23°C) with negligible shrinkage. Vacuum degassing is recommended to minimize air bubbles in cured rubber.

General Information					
Features	Good Flexibility				
	Good Strength				
	Good Stretchability				
	Good Tear Strength				
	Low Shrinkage				
	Paintable				
	Soft				
Uses	Modeling Material				
	Prosthetics				
Appearance	Translucent				
Forms	Liquid				
Processing Method	Casting				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.07	g/cm³	ASTM D1475		
Specific Volume	0.932	cm³/g	ASTM D1475		
Mixing Ratio	1A:1B by volume or weight				
Operating Temperature	-54 to 232	°C			
Molding Shrinkage - Flow	< 0.10	%	ASTM D2566		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A)	10		ASTM D2240		
Elastomers	Nominal Value	Unit	Test Method		
Tensile Stress (100% Strain)	0.152	MPa	ASTM D412		
Tensile Strength (Break)	3.28	МРа	ASTM D412		
Tensile Elongation (Break)	1000	%	ASTM D412		

Tear Strength ¹	17.9	kN/m	ASTM D624
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	> 14	kV/mm	ASTM D149
Thermoset	Nominal Value	Unit	Test Method
Pot Life	8.0	min	ASTM D2471
Thermoset Mix Viscosity	23000	сР	ASTM D2393
Demold Time	75	min	
NOTE			
1	Die B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

