

Baydur® 660 IBS (30 pcf)

Polyurethane (MDI)

Covestro - PUR

Message:

Baydur 660 IBS is a black-pigmented, rigid polyurethane structural foam system used in the reaction injection molding (RIM) process. This system incorporates a specially engineered interactive blowing system (IBS) and is supplied as two reactive liquid components. Component A is a polymeric diphenylmethane diisocyanate (PMDI), and Component B is a formulated polyol system containing no CFC- or HCFC-blowing additives. Note: Component B should be agitated thoroughly prior to delivery of contents of the drum to the day tank due to possible pigment settling. The Baydur 660 IBS system was designed for general-purpose applications and is used in industrial and recreational markets. The applications typically take advantage of the material's strength, excellent surface finish, and large part capability. As with any product, use of the Baydur 660 IBS system in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

General Information			
Features	Good strength		
	General		
	Excellent appearance		
Uses	Structural Foam		
	Industrial application		
	General		
Appearance	Black		
Processing Method	Reaction Injection Molding (RIM)		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.319	g/cm ³	ASTM D792
Molding Shrinkage - Flow (6.35 mm)	0.30 - 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw D, 6.35mm	37		ASTM D2240
Shaw D, 12.7mm	39		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Fracture, 6.35mm	6.07	MPa	ASTM D638
Fracture, 12.7mm	6.21	MPa	ASTM D638
Tensile Elongation			ASTM D638
Fracture, 6.35mm	7.0	%	ASTM D638
Fracture, 12.7mm	9.0	%	ASTM D638
Flexural Modulus			ASTM D790
6.35 mm	303	MPa	ASTM D790
12.7 mm	248	MPa	ASTM D790
Flexural Strength			ASTM D790
6.35 mm	8.27	MPa	ASTM D790

12.7 mm	8.96	MPa	ASTM D790
Compressive Strength			ASTM D695
6.35 mm	6.07	MPa	ASTM D695
12.7 mm	3.79	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength ¹	5.3	kJ/m ²	Internal method
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.35mm	77.0	°C	ASTM D648
0.45 MPa, unannealed, 12.7mm	96.0	°C	ASTM D648
Thermoset	Nominal Value		
Thermoset Components			
Component a	Mixing ratio by weight: 120		
Component B	Mixing ratio by weight: 100		
Additional Information			
Part A			
Type: Isocyanate			
Appearance: Dark brown liquid			
Specific Gravity @ 25°C: 1.24			
Viscosity @25°C: 200 cps			
Flash Point PMCC: 199°C			
NCO: 31.0 min wt%			
Part B			
Type: Polyol			
Appearance: Black liquid			
Specific Gravity @ 25°C: 1.05			
Viscosity @25°C: 2000 cps			
Flash Point PMCC: 131°C			
Water: 0.64 wt%			
Material Temperatures: 32 to 35°C			
Mold Temperature: 55 to 66°C			
Hand Mix Reactivity at 25°C			
Cream Time: 22 to 34 sec			
Gel Time: 46 to 58 sec			
Tack Free Time: 58 to 80 sec			
Free-Rise Density: 7.5 to 9.0 lb/ft ³			
Polyol Nucleation Specific Gravity: 0.85 to 0.95			
0Recommended Shot Time: 5 to 6 sec			
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT