# TAISOX 7200F

## High Density Polyethylene

### Formosa Plastics Corporation

#### Message:

TAISOX 7200F is a high density polyethylene material. This product is available in North America, Europe or Asia Pacific region. The processing method is injection molding. The main characteristics of TAISOX 7200F are: rapid prototyping cycle. Typical application areas include: container textile/fiber home apps bottle

| General Information                  |                     |          |             |
|--------------------------------------|---------------------|----------|-------------|
| Features                             | High density        |          |             |
|                                      | Fast molding cycle  |          |             |
|                                      | Good liquidity      |          |             |
|                                      |                     |          |             |
| Uses                                 | Thin wall container |          |             |
|                                      | Household goods     |          |             |
|                                      | Bottle              |          |             |
|                                      | Food container      |          |             |
|                                      | Fiber               |          |             |
|                                      |                     |          |             |
| Forms                                | Particle            |          |             |
| Processing Method                    | Injection molding   |          |             |
| Physical                             | Nominal Value       | Unit     | Test Method |
| Density                              | 0.955               | g/cm³    | ASTM D1505  |
| Melt Mass-Flow Rate (MFR) (190°C/2.1 | 6                   |          |             |
| kg)                                  | 22                  | g/10 min | ASTM D1238  |
| Hardness                             | Nominal Value       | Unit     | Test Method |
| Durometer Hardness (Shore D)         | 67                  |          | ASTM D2240  |
| Mechanical                           | Nominal Value       | Unit     | Test Method |
| Tensile Strength                     |                     |          | ASTM D638   |
| Yield                                | 27.9                | MPa      | ASTM D638   |
| Fracture                             | 14.7                | MPa      | ASTM D638   |
| Tensile Elongation (Break)           | 700                 | %        | ASTM D638   |
| Impact                               | Nominal Value       | Unit     | Test Method |
| Tensile Impact Strength              | 93.2                | kJ/m²    | ASTM D1822  |
| Thermal                              | Nominal Value       | Unit     | Test Method |
| Brittleness Temperature              | -70.0               | °C       | ASTM D746   |
| Vicat Softening Temperature          | 125                 | °C       | ASTM D1525  |
| Melting Temperature                  | 133                 | °C       |             |

| Additional Information Notched Izod Impact Strength, ASTM D256: 3.5 kg-cm/cm <sup>2</sup> |           |    |  |  |
|-------------------------------------------------------------------------------------------|-----------|----|--|--|
|                                                                                           |           |    |  |  |
| Processing (Melt) Temp                                                                    | 250 - 270 | °C |  |  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

