

Celanex® 1400FC

Polybutylene Terephthalate

Celanese Corporation

Message:

Celanex 1400FC is a general purpose, unreinforced polybutylene terephthalate with a good balance of mechanical properties and processability for use in food contact applications. Celanex 1400FC is a high flow material.

General Information			
UL YellowCard	E45575-239356		
Features	Workability, good		
	High liquidity		
	Compliance of Food Exposure		
	General		
Uses	Non-specific food applications		
	General		
RoHS Compliance	Contact manufacturer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)	50	g/10 min	ASTM D1238
Molding Shrinkage			
Flow	1.8 - 2.0	%	ASTM D955
Flow direction	1.8 - 2.0	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	72		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ISO 527-2/1A/1
Tensile Strength			
Yield, 23°C	55.2	MPa	ASTM D638
Yield	60.0	MPa	ISO 527-2/1A/50
Fracture, 23°C	55.2	MPa	ASTM D638
Tensile Strain			
Yield	4.0	%	ISO 527-2/1A/50
Fracture, 23°C	50	%	ASTM D638
Nominal Tensile Strain at Break	38	%	ISO 527-2/1A/50
Flexural Modulus (23°C)	2200	MPa	ISO 178
Flexural Stress (23°C)	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	3.7	kJ/m ²	ISO 180/1A

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	142	°C	ISO 75-2/B
0.45 MPa, annealed	154	°C	ASTM D648
1.8 MPa, not annealed	54.4	°C	ASTM D648
1.8 MPa, not annealed	58.0	°C	ISO 75-2/A
Glass Transition Temperature ¹	60.0	°C	ISO 11357-2
Melting Temperature ²	225	°C	ISO 11357-3, ASTM D3418
CLTE - Flow	1.1E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257, IEC 60093
Dielectric Strength			
-- ³	16	kV/mm	ASTM D149
--	15	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	3.20		IEC 60250
Dissipation Factor			
1 kHz	1.0E-3		ASTM D150
1 MHz	0.020		IEC 60250
Arc Resistance	190	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
--	HB		UL 94
0.750 mm	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 - 130	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	20.0 - 50.0	°C	
Rear Temperature	230 - 240	°C	
Middle Temperature	235 - 250	°C	
Front Temperature	235 - 250	°C	
Nozzle Temperature	250 - 260	°C	
Processing (Melt) Temp	235 - 260	°C	
Mold Temperature	65.0 - 93.0	°C	
Injection Rate	Moderate-Fast		
Injection instructions			
Manifold Temperature: 250 to 260°CZone 4 Temperature: 240 to 260°CFeed Temperature: 230 to 240°C			
NOTE			
1.	10°C/min		
2.	10°C/min		
3.	Method A (short time)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

