

KOPA® KN3322V0BL

Polyamide 66
Kolon Plastics, Inc.

Message:

KOPA® KN3322V0BL is a Polyamide 66 (Nylon 66) product. It is available in Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

- Flame Rated
- Flame Retardant
- Halogen Free
- Impact Resistant
- Medium Viscosity

General Information			
UL YellowCard	E190675-100647271		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Impact Resistance		
	Halogen Free		
	Medium Viscosity		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.29	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.3 to 1.6	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.60	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	80.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	15	%	ASTM D638
Flexural Modulus (23°C)	3140	MPa	ASTM D790
Flexural Strength (23°C)	132	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648A
0.45 MPa, Unannealed	235	°C	
1.8 MPa, Unannealed	105	°C	
Peak Melting Temperature	255	°C	ASTM D3418
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method

Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.40		ASTM D150
Arc Resistance	125	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

