

Karina BLACK COLOR CONCENTRATE MBU -E 48/ 1-IE

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

CARBON BLACK CONCENTRATE RECOMMENDED FOR APPLICATION IN POLYOLIFINS AND POLYOLEFINC AND PVC COMPOUNDS FOR GENERAL PURPOSES. RECOMMENDED USAGE OF 2 TO 4%.

General Information			
Additive	Carbon Black		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.50 to 1.60	g/cm ³	ASTM D792
Cadmium Content	< 50	ppm	IEC 62321
Chromium Content	< 100	ppm	IEC 62321
Color	OK		ME 12
Mercury Content	< 100	ppm	IEC 62321
Bromine Content	< 100	ppm	IEC 62321
Carrier Resin	EVA		
Lead Content	< 100	ppm	IEC 62321
Masterbatch Moisture	< 0.15	%	ME 52
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	48 to 52		ASTM D2240
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ²	> 1.0E+14	ohms·cm	ASTM D257
NOTE			
1.	24 hr		
2.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT