

# NEFTEKHIM PP 8300H

Polypropylene Copolymer  
Nizhnekamskneftekhim Inc.

Message:

Product obtained by copolymerization of propylene and ethylene in presence of complex metalorganic catalysts.  
It incorporates increased long-term thermal stability, thermal-oxidative degradation resistance when PP is produced, processed and PP-made articles are exploited, improved antistatic properties to produce articles.  
Application: corrugated plate, blow molding, jet molding.  
Technical requirements: TU 2211-136-05766801-2006

General Information	
Additive	Antistatic Nucleating Agent
Features	Antistatic Block Copolymer Good Thermal Stability Nucleated Oxidation Resistant
Uses	Corrugated Sheet
Forms	Pellets
Processing Method	Blow Molding Injection Molding Sheet Extrusion

Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	
Apparent Density	0.48 to 0.60	g/cm <sup>3</sup>	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.5 to 2.4	g/10 min	ASTM D1238
Ash Content	0.025 to 0.050	%	
Thermal Creep Temperature <sup>1</sup>	64 to 90	°C	
Thermal-oxidative Deterioration (150°C)	15.0	day	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	40 to 88		
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1150	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	50	J/m	
23°C	200	J/m	

Thermal	Nominal Value	Unit
Vicat Softening Temperature <sup>2</sup>	126 to 150	°C
NOTE		
1.	at load 0.46 H/mm <sup>2</sup>	
2.	in liquid medium under force 10 H	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

