Chemical Resources RPP 200CW

Polypropylene Random Copolymer

Chemical Resources, Inc.

Message:

RPP200CW is a clarified random copolymer polypropylene with antistat .Typical applications include Sheet Extrusion, Thermoforming, Blow Molding. RPP200CW meets the requirements of the FDA regulation 21CFR.1520

| General Information | | | |
|--|---------------------------|----------|-------------|
| Additive | Antistatic | | |
| | Clarifier | | |
| | | | |
| Features | Antistatic | | |
| | Food Contact Acceptable | | |
| | High Clarity | | |
| | Random Copolymer | | |
| | | | |
| Uses | Blow Molding Applications | | |
| | Sheet | | |
| | | | |
| Agency Ratings | FDA 21 CFR 177.1520 | | |
| Processing Method | Blow Molding | | |
| | Sheet Extrusion | | |
| | Thermoforming | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | |
| kg) | 2.0 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 24.8 | MPa | ASTM D638 |
| Tensile Elongation (Yield) | 12 | % | ASTM D638 |
| Flexural Modulus | 1100 | МРа | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C) | 85 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (0.45 MPa, Unannealed) | 79.4 | °C | ASTM D648 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

