

KOPLA PA6 KNP1100

Polyamide 6

KOPLA Co., Ltd.

Message:

KOPLA PA6 KNP1100 is a Polyamide 6 (Nylon 6) material. It is available in Asia Pacific for injection molding.

Important attributes of KOPLA PA6 KNP1100 are:

Flame Rated

Good Mold Release

Mold Release Agent

Typical applications include:

Electrical/Electronic Applications

Engineering/Industrial Parts

General Information			
Additive	Mold Release		
Features	Good Mold Release		
Uses	Belts/Belt Repair		
	Bobbins		
	Connectors		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.90 to 1.6	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.7	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	73.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	120	%	ASTM D638
Flexural Modulus (23°C)	2650	MPa	ASTM D790
Flexural Strength (23°C)	108	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	175	°C	
1.8 MPa, Unannealed	60.0	°C	
Melting Temperature	220	°C	
CLTE - Flow	8.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14 to 1.0E+15	ohms · cm	ASTM D257

Dielectric Strength	19	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	2.80		ASTM D150
Dissipation Factor (1 MHz)	0.030		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

