

RAMTOUGH RZ320G2/RZ321G2

Polycarbonate
Polyram Ram-On Industries

Message:
10% GLASS FIBER REINFORCED, FLAME RETARDANT POLYCARBONATE FOR INJECTION MOULDING APPLICATIONS

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Additive	Flame retardancy		
Features	Flame retardancy		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	17	g/10 min	ASTM D1238, ISO 1133
Water Absorption			
Saturation	0.12	%	ASTM D570
Saturated, 23°C	0.12	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2700	MPa	ASTM D638, ISO 527-2
Tensile Strength (Yield)	60.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	10	%	ASTM D638, ISO 527-2
Flexural Modulus	2800	MPa	ASTM D790, ISO 178
Flexural Strength	90.0	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	95	J/m	ASTM D256
23°C	9.5	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, not annealed	147	°C	ASTM D648, ISO 75-2/B
1.8 MPa, not annealed	135	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	148	°C	ASTM D1525, ISO 306
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Dielectric Strength	30	kV/mm	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0 - 5.0	hr	

Suggested Max Moisture	0.020	%
Rear Temperature	270 - 290	°C
Middle Temperature	280 - 300	°C
Front Temperature	290 - 310	°C
Processing (Melt) Temp	270 - 310	°C
Mold Temperature	80.0 - 120	°C
Injection Pressure	70.0 - 107	MPa
Holding Pressure	35.0 - 85.0	MPa
Back Pressure	0.350 - 0.700	MPa
Screw Speed	60 - 90	rpm

Injection instructions

Fill Speed: 25 to 50 mm/sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

