Kumho KNB NdBR-40

Acrylonitrile Butadiene Rubber

Korea Kumho Petrochemical Co., Ltd.

Message:

Kumho NdBR is ultra high cis polybutadiene rubber, produced by 1, 3-butadiene polymerization with a novel neodymium catalyst. They have more than 97% of 1,4-cis content.

Very low glass transition temperature around -100?

General Information			
Physical	Nominal Value	Unit	Test Method
Mooney Viscosity			ASTM D1646
1	43	MU	
2	65	MU	
Ash Content	< 0.50	%	ASTM D5667
CIS Content	> 97	%	Internal Method
Volatile Matter	< 0.50	%	ASTM D5668
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (300% Strain)	9.81	MPa	ASTM D412
Tensile Strength (Break)	21.6	MPa	ASTM D412
Tensile Elongation (Break)	520	%	ASTM D412
NOTE			
1.	Raw, ML1+4 at 100°C		
2.	Compund, ML1+4 at 100°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

