

OnFlex™ S EH 80A-3S7005

Thermoplastic Elastomer

PolyOne Corporation

Message:

OnFlex™-S EH thermoplastic elastomer polymer is mixed with hydrogenated styrene block copolymer. In addition to having OnFlex™The main characteristics of-S products, such as high hardness, good mechanical properties, good processability, good coloring properties, and a large operating temperature range, this series of polymers has excellent cost performance. OnFlex™-S EH polymer is filled with other substances, so it is opaque and has a relatively high density.

General Information			
Features	Good UV resistance		
	General		
Uses	Electrical appliances		
	Industrial application		
	Application in Automobile Field		
	General		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	80		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Abrasion Loss	311	mm ³	DIN 53516
Fogging (100°C)	1.5	mg	DIN 75201B
Odor rating	2.50		VDA 270
General Material Type	Styrene thermoplastic elastomers (TES)		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% strain	3.50	MPa	ISO 37
300% strain	4.50	MPa	ISO 37
Tensile Stress (Break)	7.00	MPa	ISO 37
Tensile Elongation (Break)	500	%	ISO 37
Tear Strength	33	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	39	%	ISO 815
70°C, 22 hr	70	%	ISO 815
100°C, 22 hr	88	%	ISO 815

Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index (2.00 mm)	700	°C	IEC 60695-2-12
Additional Information	Nominal Value		Test Method

各项属性值是采用注射模制基板测量得出.

Injection	Nominal Value	Unit
Processing (Melt) Temp	180 - 220	°C
Mold Temperature	30.0 - 60.0	°C
Injection Rate	Fast	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

