

# ALTECH® PP-B A 4430/120 MR30 UV

Polypropylene Copolymer

ALBIS PLASTIC GmbH

## Message:

ALTECH® PP-B A 4430/120 MR30 UV is a Polypropylene Copolymer (PP Copolymer) product filled with 20% calcium carbonate and 10% talc. It is available in Asia Pacific, Europe, or North America. Applications of ALTECH® PP-B A 4430/120 MR30 UV include appliances and housings.

Characteristics include:

REACH Compliant

RoHS Compliant

Copolymer

UV Stabilized

General Information			
Filler / Reinforcement	Calcium Carbonate,20% Filler by Weight		
	Talc,10% Filler by Weight		
Additive	UV Stabilizer		
Features	Copolymer		
Uses	Appliances		
	Housings		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.15	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	16.0	cm³/10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2400	MPa	ISO 527-2
Tensile Stress (Break)	20.0	MPa	ISO 527-2
Tensile Strain (Break)	30	%	ISO 527-2
Flexural Stress	35.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	55	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	75.0	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index (1.00 mm)	750	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature			
Circulation Dryer	80.0 to 120	°C	

Desiccant Dryer	80.0 to 120	°C
Drying Time		
Circulation Dryer	2.0 to 4.0	hr
Desiccant Dryer	2.0 to 3.0	hr
Processing (Melt) Temp	200 to 270	°C
Mold Temperature	20.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

