

Badamid® LA70 GF50 H MoS2 1%

Polyamide 66

Bada AG

Message:

Badamid® LA70 GF50 H MoS2 1% is a Polyamide 66 (Nylon 66) material filled with 50% glass fiber. It is available in Europe. Primary attribute of Badamid® LA70 GF50 H MoS2 1%: Flame Rated.

General Information				
Filler / Reinforcement		Glass Fiber,50% Filler by Weight		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.55	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturation, 23°C	4.0	--	%	
Equilibrium, 23°C, 50% RH	1.2	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	16800	12500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	230	180	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.5	3.5	%	ISO 527-2/5
Flexural Stress (23°C)	360	300	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	13	--	kJ/m ²	
23°C	18	25	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	85	--	kJ/m ²	
23°C	95	100	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	250	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	250	--	°C	ISO 75-2/A
Melting Temperature (DSC) 1	262	--	°C	ISO 3146
CLTE				DIN 53752
Flow	1.3E-5	--	cm/cm/°C	
Transverse	5.5E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+13	1.0E+10	ohms · cm	IEC 60093

Dissipation Factor (1 MHz)	0.015	0.30		IEC 60250
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.800 mm	HB	--		
1.60 mm	HB	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	2.0 to 4.0		hr	
Processing (Melt) Temp	285 to 305		°C	
Mold Temperature	80.0 to 110		°C	
NOTE				
1.	10 K/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

