Verolloy A1500

Acrylonitrile Butadiene Styrene + Nylon

PlastxWorld Inc.

Message:

Verolloy A1500 is an Acrylonitrile Butadiene Styrene + Nylon (ABS+Nylon) product. It is available in Europe or North America. Characteristics include: Flame Rated High Strength Impact Resistant

| General Information | | | | |
|-------------------------------------|--------------|------------------------|-------|-------------|
| UL YellowCard | | E315545-100091177 | | |
| Features | | High Impact Resistance | | |
| | | High Tensile Strength | | |
| | | | | |
| Forms | | Pellets | | |
| Physical | Dry | Conditioned | Unit | Test Method |
| Specific Gravity | 1.06 | | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow | 0.60 to 0.80 | | % | ASTM D955 |
| Water Absorption (24 hr) | 0.70 | | % | ASTM D570 |
| Mechanical | Dry | Conditioned | Unit | Test Method |
| Tensile Strength (Break) | 42.1 | 31.0 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 180 | 200 | % | ASTM D638 |
| Flexural Modulus | 1790 | 1170 | MPa | ASTM D790 |
| Flexural Strength | 60.7 | 39.3 | MPa | ASTM D790 |
| Impact | Dry | Conditioned | Unit | Test Method |
| Notched Izod Impact | | | | ASTM D256 |
| | | 850 | J/m | |
| 23°C, 3.18 mm | 800 | | J/m | |
| Thermal | Dry | Conditioned | Unit | Test Method |
| Deflection Temperature | | | | |
| Under Load (1.8 MPa, Unannealed) | 83.9 | 80.0 | °C | ASTM D648 |
| Flammability | Dry | Conditioned | | Test Method |
| Flame Rating (1.50 mm) | НВ | | | UL 94 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

