

# Electrafil® J-1200/CF/10

Acrylonitrile Butadiene Styrene

Techmer Engineered Solutions

## Message:

Electrafil® J-1200/CF/10 is an acrylonitrile butadiene styrene (ABS) product, which contains a filler of 10% carbon fiber reinforcement. It can be processed by injection molding and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Electrafil® The application fields of J-1200/CF/10 include packaging, engineering/industrial accessories, automobile industry, commercial/office supplies and conveyor belts.

Features include:

flame retardant/rated flame

ROHS certification

Conductivity

General Information			
Filler / Reinforcement	Carbon fiber reinforced material, 10% filler by weight		
Features	Conductivity		
	Antistatic property		
Uses	Packaging		
	Bushing		
	Conveyor accessories		
	Automotive Electronics		
	Business equipment		
RoHS Compliance	RoHS compliance		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.10	%	ASTM D955
Water Absorption (24 hr)	0.40	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	7580	MPa	ASTM D638
Tensile Strength (Break, 23°C)	82.7	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	1.7	%	ASTM D638
Flexural Modulus (23°C)	6890	MPa	ASTM D790
Flexural Strength (Break, 23°C)	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	43	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.18 mm)	190	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, not annealed	104	°C	ASTM D648
1.8 MPa, not annealed	98.9	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+2	ohms	ASTM D257
Volume Resistivity	50	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
Additional Information			
Surface Resistivity, ASTM D257: 1E2-1E3 ohms/sqVolume Resistivity, ASTM C611: 10-100 ohm-cm			
Injection	Nominal Value	Unit	
Drying Temperature	76.7 - 87.8	°C	
Drying Time	2.0 - 16	hr	
Rear Temperature	216 - 232	°C	
Middle Temperature	221 - 238	°C	
Front Temperature	210 - 221	°C	
Nozzle Temperature	199 - 221	°C	
Processing (Melt) Temp	232 - 260	°C	
Mold Temperature	71.1 - 87.8	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

