

Starflam RF0059

Polyamide 66

Eurostar Engineering Plastics

Message:

Starflam RF0059 is a Flame Retardant, Glass Fiber Reinforced, Polyamide 66 Injection Molding Resin

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Flame Retardant		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.20 to 0.30	%	Internal Method
Water Absorption (Saturation, 23°C)	4.5	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9100	MPa	ISO 527-2/1
Tensile Stress (Break)	150	MPa	ISO 527-2/5
Tensile Strain (Break)	2.0	%	ISO 527-2/5
Flexural Modulus ²	8900	MPa	ISO 178
Flexural Stress	215	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ³			ISO 180/1A
-20°C	6.0	kJ/m ²	
23°C	7.0	kJ/m ²	
Unnotched Izod Impact Strength ⁴ (23°C)	60	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵			
0.45 MPa, Unannealed, 100 mm Span	256	°C	ISO 75-2/Be
1.8 MPa, Unannealed, 100 mm Span	240	°C	ISO 75-2/Ae
Vicat Softening Temperature	255	°C	ISO 306/B120
CLTE			ISO 11359-2
Flow : 23 to 60°C	3.0E-5	cm/cm/°C	
Transverse : 23 to 60°C	9.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm, Tested by E2P)	V-0		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	

Drying Temperature	75.0 to 85.0	°C
Drying Time	4.0 to 6.0	hr
Suggested Max Moisture	0.20	%
Rear Temperature	270 to 290	°C
Middle Temperature	270 to 280	°C
Front Temperature	270 to 280	°C
Processing (Melt) Temp	270 to 280	°C
Mold Temperature	70.0 to 80.0	°C

NOTE

1.	Tensile Bar
2.	2.0 mm/min
3.	80*10*4
4.	80*10*4
5.	120*10*4

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

