RTP 201D UV

Polyamide 612

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue' The data for this material has not been recently verified.

Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Glass Fiber, 10% Filler by Weight		
RoHS Compliance	Contact Manufacturer		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm³	ASTM D792
Molding Shrinkage - Flow			ASTM D955
3.18 mm, Injection Molded	0.60	%	
6.35 mm, Injection Molded	0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	4130	MPa	ASTM D638
Tensile Strength	76.0	MPa	ASTM D638
Tensile Elongation (Yield, Injection Molded)	3.0	%	ASTM D638
Flexural Modulus (Injection Molded)	3790	MPa	ASTM D790
Flexural Strength (Injection Molded)	124	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm, Injection Molded)	59	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	420	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, Injection Molded	207	°C	
1.8 MPa, Unannealed, Injection Molded	202	°C	
Injection	Nominal Value	Unit	
Rear Temperature	252 to 279	°C	
Middle Temperature	252 to 279	°C	
Front Temperature	252 to 279	°C	
Mold Temperature	60.0 to 93.0	°C	

Injection Pressure 69.0 to 124 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

