# **DJSilicone NE-280**

#### Silicone

### DONGJUE SILICONE (NANJING) CO., LTD

#### Message:

This product could be put into basic processing after adding vulcanizator DCBP. And it may not need second vulcanization when technical conditions properly controlled. The formed product has the following properties: very good high and low temperature resistance, corona and arc resistance, and electric insulation. It is suitable for different kinds of electric wire and cable, jacket rubber tubes and parts for electrical insulator, heat-resistant seals, irregular shaped and foam strips.

General Information				
Features	Arc Resistant			
	Electrically Insulating			
	High Heat Resistance			
	Low Temperature Resistant			
Uses	Foam			
	Seals			
	Tubing			
	Wire & Cable Applications			
Appearance	Clear/Transparent			
	White			
Processing Method	Extrusion			
Physical	Nominal Value	Unit	Test Method	
Density	1.20 to 1.30	g/cm³	ASTM D1505	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	78 to 82		ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Set <sup>1</sup>	< 10	%	ASTM D412	
Tensile Strength <sup>2</sup> (Yield)	> 7.00	MPa	ASTM D412	
Tensile Elongation			ASTM D412	
Break <sup>3</sup>	> 150	%		
Break <sup>4</sup>	> 180	%		
Tear Strength	> 20.0	kN/m	ASTM D624	
Electrical	Nominal Value	Unit	Test Method	
Volume Resistivity	> 3.0E+14	ohms·cm	ASTM D257	
Dielectric Strength	> 20	kV/mm	ASTM D149	
NOTE				
1.	For Line			
2.	For Line			

3.	For Tube
1	For line

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

