

# InnoClear™ OC-7085

Polyurethane Thermoset Elastomer

Innovative Polymers, Inc.

Message:

OC-7085 is a water-clear, semi-rigid polyurethane formulated for room temperature hand batch or vacuum assisted casting methods. Excellent physical properties can be obtained with a room temperature cure without the utilization of mercury, MOCA or TDI The unique chemistry of OC-7085 imparts excellent optical clarity as well as UV stability. This material has been specially formulated for mass castings into either tin or platinum silicone molds.

General Information			
Features	Good UV Resistance		
	High Clarity		
RoHS Compliance	RoHS Compliant		
Appearance	Clear/Transparent		
Processing Method	Vacuum Casting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
Cured	1.10	g/cm³	
Hardener	1.10	g/cm³	
Base Resin	1.13	g/cm³	
Molding Shrinkage - Flow	0.10 to 0.50	%	ASTM D2566
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	2380	MPa	ASTM D790
Flexural Strength	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	95.0	°C	
1.8 MPa, Unannealed	91.0	°C	
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Volume: 59		
Hardener	Mix Ratio by Weight: 57		
	Mix Ratio by Weight: 100		
Resin	Mix Ratio by Volume: 100		

Demold Time	960 to 1400	min	
Additional Information	Nominal Value	Unit	Test Method
Peak Exotherm - 200g mass	52	°C	
Uncured Properties	Nominal Value	Unit	Test Method
Viscosity			
25°C <sup>1</sup>	0.45	Pa·s	
25°C <sup>2</sup>	0.65	Pa·s	
25°C <sup>3</sup>	1.3	Pa·s	
Curing Time <sup>4</sup>	40	hr	
Gel Time	80 to 1.2E+2	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	75 to 85		ASTM D2240
Tensile Modulus	1830	MPa	ASTM D638
Tensile Strength	72.4	MPa	ASTM D638
Tensile Elongation at Break	8.0	%	ASTM D638
NOTE			
1.	Resin		
2.	Mixed		
3.	Hardener		
4.	24 hours at 77°F + 16 hours at 150°F		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT