

PONACOM ABS 7315

Acrylonitrile Butadiene Styrene

Ponachem Compound GmbH

Message:

PONACOM ABS 7315 is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Europe.

General Information			
Features	Medium Flow		
Appearance	Black		
Forms	Granules		
Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/10.0 kg)	14 to 16	g/10 min	ISO 1133
Water Absorption (Saturation, 23°C)	1.6	%	DIN 53495
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2200	MPa	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0 to 11	kJ/m ²	ISO 179/2C
Notched Izod Impact Strength (23°C)	10 to 13	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	92.0	°C	ISO 306/B50
Melting Temperature	210 to 240	°C	
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT