# Novamid® 1030J

## Polyamide 6

## **DSM Engineering Plastics**

#### Message:

Novamid® 1030J is a Polyamide 6 (Nylon 6) material. It is available in Asia Pacific for extrusion. Primary attribute of Novamid® 1030J: Flame Rated.

General Information			
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm³	ISO 1183
Water Absorption (Equilibrium, 23	°C, 50%		
RH)	2.8	%	ISO 62
Viscosity Number	245	cm³/g	ISO 307
Thermal	Nominal Value	Unit	Test Method
Melting Temperature <sup>1</sup>	220	°C	ISO 11357-3
Flammability	Nominal Value		Test Method
Flammability Classification			IEC 60695-11-10, -20
0.810 mm	V-2		
1.50 mm	V-2		
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

