

HAIPLEN EP50 Z3

Polypropylene Copolymer

Taro Plast S.p.A.

Message:

PP block copo - impact modified
Available: all colors, UV stabilized (L), heat stabilized (H)

General Information			
Additive	Heat Stabilizer		
	Impact Modifier		
	UV Stabilizer		
Features	Copolymer		
	Good UV Resistance		
	Heat Stabilized		
	Impact Modified		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			ASTM D955
Flow	1.5	%	
Across Flow	1.5	%	
Granule Humidity	0.050	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	20.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	> 150	%	ASTM D638, ISO 527-2
Flexural Modulus	850	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	> 500	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	47.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature			
--	151	°C	ASTM D1525, ISO 306/A 2 ¹
--	55.0	°C	ASTM D1525, ISO 306/B 3 ²

Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Oxygen Index	21	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	1.0	hr	
Processing (Melt) Temp	190 to 230	°C	
Mold Temperature	30.0 to 50.0	°C	
Injection Rate	Fast		
NOTE			
1.	Loading 1 (10 N)		
2.	Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

