

# Cri-Line LC-815-85

Fluoroelastomer

Cri-Tech, Inc.

## Message:

66% Fluorine copolymers formulated for low cost. LC compounds are used in lathe cut and custom molded goods, including value stem seals.

General Information		
Features	Copolymer	
Uses	Seals	
Physical	Nominal Value	Unit
Specific Gravity	1.85	g/cm <sup>3</sup>
Fluorine Content	66	%
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	84	
Elastomers	Nominal Value	Unit
Tensile Stress (100% Strain)	9.65	MPa
Tensile Strength	13.8	MPa
Tensile Elongation (Break)	140	%
Compression Set <sup>1</sup> (200°C, 22 hr)	18	%
NOTE		
1.	Plied discs	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT