## EPO-TEK® H20E-SLR

## Epoxy; Epoxide

Epoxy Technology Inc.

## Message:

EPO-TEK® H20E-SLR is a two-component, electrically conductive, epoxy adhesive designed for solar ribbon bonding of photovoltaic modules. It provides the electrical back-contact for ribbon stringing of solar cells into modules and panels.

General Information			
Features	Electrically Conductive		
	Fast Cure		
	Thixotropic		
Uses	Adhesives		
	Electrical/Electronic Applications		
	Solar Panels		
Agency Ratings	EC 1907/2006 (REACH)		
	EU 2003/11/EC		
	EU 2006/122/EC		
RoHS Compliance	RoHS Compliant		
Forms	Paste		
Physical	Nominal Value	Unit	
Particle Size	< 20.0	μm	
Degradation Temperature	388	°C	
Die Shear Strength - >10 kg (23°C)	23.4	MPa	
Operating Temperature			
Continuous	-55 to 200	°C	
Intermittent	-55 to 300	°C	
Storage Modulus	7.18	GPa	
Thixotropic Index	3.30		
Weight Loss on Heating			
200°C	0.61	%	
250°C	2.0	%	
300°C	3.5	%	
Thermal	Nominal Value	Unit	
Glass Transition Temperature <sup>1</sup>	81.0	°C	
CLTE - Flow			
<sup>2</sup>	4.8E-5	cm/cm/°C	
3	2.3E-4	cm/cm/°C	

Thermal Conductivity	1.2	W/m/K	
Thermoset	Nominal Value	Unit	
Thermoset Components			
Part A	Mix Ratio by Weight: 10		
Part B	Mix Ratio by Weight: 8.0		
Shelf Life (23°C)	52	wk	
Uncured Properties	Nominal Value	Unit	
Color			
4	Silver		
5	Silver		
Density			
Part A	1.96	g/cm³	
Part B	2.43	g/cm³	
Viscosity <sup>6</sup> (23°C)	4.4	Pa·s	
Curing Time (140°C)	0.17	hr	
Pot Life	1200	min	
Cured Properties	Nominal Value	Unit	
Shore Hardness (Shore D)	53		
Lap Shear Strength (23°C)	7.17	MPa	
Volume Resistivity (23°C)	< 4.0E-3	ohms·cm	
NOTE			
1.	Dynamic Cure 20-200°C/ISO 25 Min; Ramp -10-200°C @ 20°C/Min		
2.	Below Tg		
3.	Above Tg		
4.	Part B		
5.	Part A		
6.	50 rpm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

