Epolene® E-14E

Low Density Polyethylene

Westlake Chemical Corporation

Message:

The Epolene E-14E is a low molecular weight, low density, oxidized polyethylene. The low molecular weight and low softening point contribute to the production of stable, low color emulsions by both atmospheric (wax-to-water) and pressure emulsification methods. Epolene E-14E imparts excellent slip resistance to floor polish films.

| General Information | | | |
|--|--|----------|-------------|
| Features | Durable | | |
| | Good Toughness | | |
| | Low Molecular Weight | | |
| | | | |
| Uses | Adhesives | | |
| | Automotive Applications | | |
| | Building Materials | | |
| | Construction Applications | | |
| | Flooring Maintenance/Repair | | |
| | | | |
| Forms | Pellets | | |
| Physical | Nominal Value | Unit | |
| Acid Number | 17.00 | mg KOH/g | |
| Molecular Weight ¹ | 3600 | | |
| Ring and Ball Softening Point | 104 | °C | ASTM E28 |
| Penetration Hardness ² (25°C) | 400 | mm | ASTM D5 |
| Fill Analysis | Nominal Value | Unit | Test Method |
| Melt Viscosity (125°C) | 225 | mPa∙s | |
| NOTE | | | |
| | Molecular weight measured via Ge | 2 | |
| 1. | Permeation Chromatography (GPC) using polystyrene standards | | |
| 2. | Needle under 100-g load for 5s, tenths of mm | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

